



We protect and
beautify the world™

PCU75153

ENVIROCRON® Powder Coat

Highlights

PPG's Enviracryl™ and Envirocron™ powder coatings are aesthetically pleasing, produce a durable uniform finish and can be custom formulated with finishes from high gloss to low gloss, and in a variety of textures.

PPG's "World Class" Polyester Urethane Powder Coatings provide a combination of good physical and chemical resistance properties. This extensive line of Polyester Urethane Powders is manufactured to meet the increasing requirement demands of the automotive and industrial markets. These sophisticated Polyester Urethanes are the solution to your smoothness, low-bake, durability and physical property requirements. An unsurpassed application development program enables consistently friendly use on a variety of substrates.

Product Features

Available in a wide range of colors and glosses

Good chemical resistance

Bonded Metallic Coating

Technical Properties

| Property | Test Method | Value |
|-------------------|-------------|-------------------------------|
| Color | | Chrome Shadow Monocoat |
| Appearance | | Smooth |
| Gloss | ASTM D-523 | 60 - 70 @ 60° |
| Adhesion | ASTM D-3359 | 100% (5B Pass) |
| Hardness | ASTM D-3363 | H - 2H Pencil (Eagle) |
| Impact Resistance | ASTM D-2794 | 40 In.-lbs. Direct |
| Conical Mandrel | ASTM D-522 | 1/8" Mandrel - No Cracking |
| Salt Spray | ASTM B-117 | 750 Hrs. Pass |
| Humidity | ASTM D-1735 | 750 Hrs. Pass |

Film Properties were determined using 2.0 - 3.0 mils powder film over zinc phosphated, non-chrome rinse pretreated, 22 gauge, unpolished cold rolled steel test panels.

Application Data

| | |
|--|--|
| Application Type: | Electrostatic Spray |
| Recommended Bake: | 15 Minutes at 375 °F Metal Temperature See Cure Curve PCU-001 |
| Specific Gravity: | 1.22 ± .05 |
| Theoretical Coverage: | 158 Sq. Ft. per pound at 1.0 mil |
| Shelf Life from Date of Manufacture (@40-60% RH): | 80 °F Maximum - 24 Months |

*PPG recommends that all material be used in FIFO order (first in - first out).
Materials that exceed the recommended shelf life should be tested prior to use.*

* Statements and methods described herein are based upon the best information and practices known to PPG Industries, Inc. ("PPG"). Any statements or methods mentioned herein are general suggestions only and are not to be construed as representations or warranties as to safety, performance, or results. Since the suitability and performance of the product is highly dependent on the product user's processes, operations, and numerous other user-determined conditions, the user is solely responsible for, and assumes all responsibility, risk and liability arising from, the determination of whether the product is suitable for the user's purposes, including without limitation substrate, application process, pasteurization and/or processing, and end use. No testing, suggestions or data offered by PPG to the user shall relieve the user of this responsibility. PPG does not warrant freedom from patent infringement in the use of any formula or process set forth herein. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin. Contact your PPG representative for the most up to date information.

ENVIROCRON and the PPG logo are registered trademarks of PPG Industries Ohio, Inc.

